

**PRIMER**

Waterborne masonry undercoat

**DESCRIPTION**

Masonry undercoat formulated with water-dispersed synthetic resins, possessing a specific technology which generates a special film that ensures secure adhesion on different types of substrates as well as insulating and consolidating capacities.

It guarantees even absorption and hence a uniform finish and excellent adhesion for subsequent coats.

Thanks to the resin and special lamellar pigments contained in the product, *Primer* guarantees high breathability, better colour resistance and fewer coats during the painting cycle.

**PERFORMANCE DATA**

	Method	Value
Opacity level (Contrast ratio)	ISO 6504-3	70%
Adhesion to substrates in building	CAP	GOOD
Water vapour permeability	CAP	Excellent
Specific weight	ISO 2811-1	1210-1310 g/l
Drying time	CAP - PF2	recoatable 5-8h;
Solid by weight	CAP - PF25	34-38 %

**SHELF LIFE**

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

**COLOUR RANGE**

White AC16

The range may be extended to the colours of the *Tucano* sample books.

The colour could vary slightly from one production batch to the next; it is therefore important to finish the job with the same batch.

**TYPICAL USE**

Apply directly as a preventive coat on old paints, alkaline substrates such as plaster with different compositions (cement, common lime, pre-mixed, skim coat plaster for exterior insulation), concrete and fibrocement in one coat. Can be recoated with Acrylic and Siloxan Texture Covering

**TOOLS**

Roller, Brush, Spray.

**THINNING**

0-40% by volume with water

**COVERAGE**

8-10 m<sup>2</sup>/l per coat.

**APPLY**

+5°C +30°C

**SPECIFICATION ITEM**

Pigmented consolidating undercoat containing water dispersed resins featuring the *Eliokem* technology to be applied directly as a preventive coat on old paints, alkaline substrates such as plaster with different compositions (cement, common lime, pre-mixed, skim coat plaster for exterior insulation), concrete and fibrocement in one coat, at an average consumption rate of 110 ml/m<sup>2</sup>. Compatible with both acrylic and siloxanic Texture covering.

## **PRIMER**

Waterborne masonry undercoat

### **INSTRUCTIONS**

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.