

DESCRIPTION

Wall paste filler suitable for filling holes and cracks on interior walls. This paste is formulated with "glass bubbles" 3M whose round shape gives them the smallest surface area with respect to their volume of other inert substances. This has allowed for the formulation of *Stucco Light* with a very low specific weight and high charge content. Thanks to these properties, after application, there is no evidence of shrinkage, cracking and reduction. It is possible to easily fill holes and cracks of various dimensions as the product requires one application only without additional passes to complete the work. It dries in a quick and homogeneous manner and does not require any pre-treatment. *Stucco Light* allows for a significant reduction in work times.

PERFORMANCE DATA

Specific weight	ISO 2811-1	White: 330-370 g/l;
Drying time	CAP - PF2	1 cm thickness: Dry to recoat 30 min. with water paints; 48h with solvent-based products.
Solid by weight	CAP - PF25	54-58 %

SHELF LIFE

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

COLOUR RANGE

White

TYPICAL USE

Different types of surfaces such as plaster, concrete, plasterboard wood in large thickness up to 2 cm with only one pass without any risk of cracking. If the product is too dry, add a few drops of water and mix. The surface requiring filling must be clean, dry and free from dust and uneven material. Apply the product using a spatula on the part that needs to be filled. *Stucco Light* can be coloured with IP dyes.

TOOLS

Spatula – press the product well and level it thoroughly in order to skip sandpapering. Use a spatula damped with water to level.

THINNING

Ready to use.

APPLY

+5°C +30°C

SPECIFICATION ITEM

Wall paste filler suitable for filling holes and cracks on interior walls, on different types of surfaces such as plaster, concrete, plasterboard wood in large thickness up to 2 cm with only one pass without any risk of cracking.

INSTRUCTIONS

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.