

PRODUCT DATA SHEET

CROMETAL
Anticorrosion fast drying undercoat

CHARACTERISTIC Paint with rust-inhibiting effect, ideal for preventing the corrosion of ferrous metal surfaces in interior and exterior.
 It is characterized by high penetration of the substrate, excellent adhesion, flexibility, provides good grip to topcoats.
 It is based on modified alkyd resins, solvent-based, ionic exchange pigments and zinc phosphate which have particularly good adhesion properties on metal and barrier effect so as to ensure high impermeability to water and an antioxidant effect; It is characterized by fast drying and resistance to the subsequent application of quick-drying enamels and alkyd enamels.

USE It is ideal for the protection of steel artifacts, new or undergoing maintenance, such as carpentry, fixtures, railings, barges, tanks, agricultural equipment, subjected to the action of corrosive agents in rural, urban industrial environments. The thickness recommended for effective protection is established depending on the aggressiveness of the environment. The preheating of the product to about 30 ° C gave good results by improving the drying, the coverage of the edges and allowing application of greater thickness for single layer. Sanding dust and / or spraying and dry paint residues should not be accumulated because they cause spontaneous combustion.

PROPERTY OF THE PRODUCT

	VALUE	METHOD
Application temperature	<+120 °C	
Flash point	27°C	
Solid by volume %	60 ± 2	
VOC	425 g/l	
Brilliance 60°	<15	
Adhesion: ISO 2409	0	UNI EN ISO 2409
Impact resistance	greater 1 Kg/20cm	UNI 8901
Bending resistance	unchanged with spindle 10mm	UNI EN ISO 1519

SPECIFICATION DATA

	VALUE	METHOD
Specific weight	1400-1500 g/l	Internal PF3
Drying Time	Fully 12 h	Internal PF2
Coverage	95-99	Internal PF11

THICKNESS AND YIELD

	Min.	Max	Recommended
Thickness of dry film, µm	40	80	60
Thickness of wet film, µm	67	135	100
Theoretical yield, m²/l	14,8	7,4	10
Theoretical yield, m²/kg	10.3	5,1	6.9

PRODUCT DATA SHEET

CROMETAL
Anticorrosion fast drying undercoat

STORAGE	Product is stable till one year as long as it is kept in original and unopened buckets at temperature between +5°C e +30°C.	
COLOUR	Yellow oxide.	
PREPARATION OF SURFACE	<p>General observation: Surface must be dry and clean from any kind of oil, grease and salts.</p> <p>New steel The surface must be clean and dry, free of oils and other contaminants. Sandblasting Sa2½ ensures the best performance corrosion.</p> <p>Surfaces treated with shop primer If undamaged, clean and free from any dirt, oil, grease, salts and dry, it can be painted otherwise perform the preparation as for coated surfaces.</p> <p>Coated surface <i>With primer:</i> it can be painted if the substrate is clean and free of dirt, oil, grease, and the application falls within the maximum re-coat time of the primer. If cleaning is required, perform pressure washing grade Wa 2 (surface free of oil, grease, salt, dirt). <i>With complete finishing coat:</i> if undamaged compatible and non-chalky perform cleaning from any oil and grease with detergent, then run sanding surface followed by pressure washing to remove dust and salts. <i>Rusty coating:</i> perform mechanical preparation St2 or St3 followed by pressure washing to remove oil, grease, dust and salt or sand blasting Sa2 or Sa2½; then restore the thickness of primer. <i>Localized maintenance:</i> perform mechanical preparation St2 or St3 followed by pressure washing to remove oil, grease, dust and salt or sand blasting Sa2 or Sa2½. Round off the edges of the well anchored painting and restore the system in the original layers and thicknesses.</p>	
TOOLS	Conventional or airless spray: Nitro NV 5000 (with high temperature and humidity <40% it is possible the formation of "dusting"; in this case use Diluente S 800), roller, brush.	
APPLICATION	Thinning Application condition Application by airless Application by conventional spray Thinner for washing	Conventional or airless spray: 5-10% by diluente Nitro NV5000 Roller, brush: 5-10% by Diluente S800 +5°C +40°C >3°C at dew point Relative humidity: < 70% Nozzle pressure: 15 MPa (150 kp/cm², 2100 psi.). Nozzle: 0,28 - 0,38mm (0,011 - 0,018") Angle range: 40 - 80° Air pressure: Compression ratio 30:1 (pressure 150-180 kg/cm²) Nozzle: 1,6 – 1,8mm Angle range: 40 - 80° Air pressure: 3,5-4 kg/cm² Diluente Nitro NV 5000
DRYING TIME	Dry time are purely indicative as it might be longer or shorter by keeping in	

PRODUCT DATA SHEET

CROMETAL
Anticorrosion fast drying undercoat

consideration ventilation, humidity, thickness of the applied film. High thicknesses per coat and unfavorable environmental conditions slow down the drying and hardening depth.

DTF 50 micron

Surface temperature

10°C

23°C

Out touch

45'

15'

Dry touch

3h

45

Full

24h

12h

Minimum time of over application

90'

45''

RECOMMENDED FINISHES

Fast drying enamels: Supersinteol Rapido, RE30;

Synthetic enamels: Gladium, Eno, Sinto 26

Micaceous iron enamels: FER RE GG16, FER GG11

RECOMMENDED SYSTEM

Rural environment

Product	Coat	Wet Thickness	Dry thickness
Crometal	1	100	60
Crometal	1	100	60
RE 30	1	90	50
Total	3	290	170

ALTERNATIVE SYSTEM

Product	Coat	Wet Thickness	Dry thickness
Crometal	1	125	75
Fer RE GG 16	1	90	50
Total	2	215	125

INSTRUCTIONS

To carry out the work in a proper way, it is needed to strictly follow the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system may vary.

This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample.