

DESCRIPTION

Water-base paint, waterproof and moderately breathable, easy to apply, ideal for professional use as it is extremely compatible. Excellent adhesion and workability properties on a wide variety of substrates.
 Ideal for interiors, odourless, formulated with acrylic resins in aqueous emulsion. Pearl effect and attractive play of light and reflections; ideal for creating special decorations with an effect that is soft touching.
 High quality guarantees maximum protection and excellent finishing. High resistance to the penetration of stains and dirt. Easy to clean, even with commercial detergents. Being odourless, it is particularly indicated for applications in poorly ventilated areas. It is made with raw materials chosen for a low impact, with reduced pollution and with minimal emissions in order to preserve the wellbeing and safety of users and people living in the environment; the product meets the requirements of the **Class A +** according to the relevant Test Report.

PROPERTY OF THE PRODUCT

	Value	Method
WATER VAPOUR DIFFUSION	Good	CAP
IMPACT RESISTANCE	Excellent	
DIRT RETENTION	Low	
RESISTANCE TO WASHING	Excellent	
SOLID BY WEIGHT	33-39%	Internal PF25

SPECIFICATION DATA

Specific weight	1070-1170 g/l	Internal PF3
Drying time	Dry to recoat 5-8h; Fully 5 days.	Internal PF2

SHELF LIFE

1 year minimum, stored in unopened and original cans at temperatures between +5°C and +30°C.

COLOUR RANGE

As per samples.
 The colour could vary slightly from one production batch to the next; it is therefore important to finish the job with the same batch.

TYPICAL USE

It is indicated as a finish to create a valuable decorative effect both for public and private places where particular decorations are desired. It is necessary to intervene on even and perfectly smooth surfaces. The Texture effect depends on the ability of the applicator and the quantity applied and therefore the sample is indicative. Before carrying out the work, carry out practical tests on a demonstration panel.
 To obtain a homogeneous surface, work with the same tool and the only operator in the finish, and ensure continuous wet-on-wet processing of the entire wall without interruptions. Mix the product 2 minutes before and after the introduction of the AC16 dyes.
 The application of the sole non-pigmented base can give rise to evident color differences, therefore the product must be applied only and exclusively after having pigmented it according to the relative color chart. Tools are washed with water immediately after use.

TOOLS

Roller, Spalter- Brush.

THINNING

Ready to use.

COVERAGE

10-12 m²/l per coat.

APPLY

+5°C +30°C

COATING SYSTEM

On various plasters, new or already painted, rough and irregular, clean the surface to be decorated by removing any parts flaking off and skim with *Jolli* or *Stuccocap* . filler. On wood, apply *Opakite* primer or *Opakite W* and sandpaper. On iron substrates, apply a coat of rust *Chromocap* or *Chromocap W*

On substrates prepared as described above and on plasterboard

1. Using a short-hair roller, apply a coat of *Absolutecap* diluted 5-10% by volume with water.
2. After 5-8 hours, using a short-hair roller apply a coat of *Pearl* ready to use, then pass the Spalter brush on the wet paint with irregular or circular movements.

Apply DECOR PROTECTIVE to increase the resistance to abrasion, scratch and washing with detergents and edible liquid.

SPECIFICATION ITEM

Acrylic paint for interiors, in aqueous dispersion, suitable for pearlescent effect finishes, with high wash resistance, to apply in a single layer, with an average consumption of 0.1 l/m² on skimmed surfaces, pre-emptively treated with a coat of *Ecolora Absolutecap*.

INSTRUCTIONS

To carry out the work in a proper way, it is strictly needed to follow up the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.