

**CHARACTERISTICS** Pigmented aqueous solution of a fungicidal agent chosen thanks to its wide range of action against different types of mould as well as its extremely low toxicity. The product covers mould stains and leaves no unpleasant residual odours.

**COMPOSITION** Synthetic fungicide dispersed in acrylic resins and selected hiding pigments.

<b>PERFORMANCE DATA</b>	METHOD	OPTIMAL VALUE
RESISTANCE TO MOULD		
SOLID BY WEIGHT	Internal PF25	21 - 25 %

<b>SPECIFICATIONS</b>	VALUE	METHOD
SPECIFIC WEIGHT	1015-1115 g/l	Internal PF3
DRYING TIME	Recoating 5-8h;	Internal PF2
HIDING POWER	> 85	Internal PF11

**SHELF-LIFE** 1 year of stability if product is stored in original container at temperatures of between +5°C and +30°C.

**COLOUR RANGE** White.

**TYPICAL USE** A1 is highly suited for application in poorly ventilated corners and domestic surfaces to treat mould on interior walls. The product is ready to use and should be applied directly on the mould using the sprayer supplied, making sure that all dark spots have been covered.  
As a preventive measure, the product can also be applied every six months to areas where mould is likely to form.  
A1 can be over-applied with products from the SANACAP and K81 lines.

**TOOLS** Sprayer. Clean the sprayer with water immediately after use.

**COVERAGE** 10-12 m<sup>2</sup>/l

**THINNING** Product is ready to use.

**APPLICATION TEMPERATURE** +5°C +30°C

**SPECIFICATION ITEM** Pigmented anti-mould system based on water-soluble fungicides to be applied on existing mould with an average consumption of 100 ml/m<sup>2</sup>.

**INSTRUCTIONS** To carry out the work a workmanlike manner, follow the instructions for surface preparation according to the CAP Arreghini Books.  
The specification data have been calculated at a temperature of +23°C with a relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary. This technical information is intended as a rough guide. Due to the extensive variety of substrates and application conditions, we suggest checking the suitability of the product and testing the effectiveness on a sample first.